

## Buffing Pad DLW and DLW R (with Ribs)

- Reference : **DLW 76 (3") & 130 (5")**
- Packaging : **9 x 50**
- Document name : **Norme E32.90.025.G**
- Fiber Composition : **100% New Zealand Wool**
- Jersey Loop Pile Composition : **Polyester**
- Color Fiber of the Pad : **Natural Wool colour**
- Color Jersey Loop pile : **Bottle Green or Black**

## Physical properties

Tests	Measure	Result	Spec Targets	Methods
Diameter	mm	76 & 130	76 & 130	
Thickness	mm	6	5.5	
Weight	g	11	11.2	
Support mass surface	g/m <sup>2</sup>	735	730	D45 1012
Tear resistance new	N/m	12	11	D41 1049
Tear resistance after 7 days at 70 °C	N/m	12	11	D41 1049
Elongation to break new	%	15	13	D41 1050
Elongation to break after 7 days at 70°C	%	15	13	D41 1050
Tensile strength	kPa	600	600	DIN EN ISO 1798

## Applications

- Fine Cropped Wool fiber ensure high gloss finish of delicately coated surfaces
- Less Hologram build up due to cooler wool temperatures compared to foams and needle-punched fabrics
- Fast finish of the surface due to vertical pile positioning maintained during polishing process, fast cut
- Time savings during polishing process due to this high performance technical wool fiber
- Special glue technology ensures permanent fix of the pad onto the attachment loop pile velours